

Status: Currently Official on 15-Feb-2025
Official Date: Official Prior to 2013
Document Type: Reagents
DocId: GUID-91CB1C3E-ACC2-42DD-B87C-946D0F75E019_1_en-US
DOI: https://doi.org/10.31003/USPNF_R2098_01_01
DOI Ref: 31463

© 2025 USPC
Do not distribute

Ion-Exchange Resin

—An intimate mixture of 4 parts of a strongly acidic cation-exchanger in the hydrogen form (produced by sulfonation of a styrene-divinylbenzene copolymer, representing 8 to 10% divinylbenzene) and 6 parts of a strongly basic anion-exchanger in the hydroxyl form (produced by amination with trimethylamine of a chloromethylated styrene-divinylbenzene copolymer, representing 3 to 5% divinylbenzene).

[NOTE—A suitable resin is “Amberlite MB-150,” available from Sigma-Aldrich, www.sigma-aldrich.com.]

Auxiliary Information - Please [check for your question in the FAQs](#) before contacting USP.

Topic/Question	Contact	Expert Committee
ION-EXCHANGE RESIN	Margareth R.C. Marques Principal Scientific Liaison	HDQ Headquarters

Most Recently Appeared In:

Pharmacopeial Forum: Volume No. Information currently unavailable

Current DocID: [GUID-91CB1C3E-ACC2-42DD-B87C-946D0F75E019_1_en-US](#)

DOI: https://doi.org/10.31003/USPNF_R2098_01_01

DOI ref: [31463](#)

OFFICIAL