

Status: Currently Official on 15-Feb-2025  
Official Date: Official as of 01-Nov-2020  
Document Type: Reagents  
DocId: GUID-5BC38CF6-D9E6-4B39-A835-56672A3E969F\_2\_en-US  
DOI: [https://doi.org/10.31003/USPNF\\_R5811\\_02\\_01](https://doi.org/10.31003/USPNF_R5811_02_01)  
DOI Ref: p8gk5

© 2025 USPC  
Do not distribute

**Add the following:**

## ^L106

—Weak cation-exchange resin consisting of ethylvinylbenzene, 55% cross-linked with divinylbenzene copolymer, 5–8 µm diameter, macroporous particles having an average pore size of 100 Å units. Substrate is surface grafted with carboxylic acid and phosphonic acid functional groups. Capacity NLT 2800 µEq/column (4-mm × 25-cm).▲ (USP 1-Aug-2020)

**Auxiliary Information** - Please [check for your question in the FAQs](#) before contacting USP.

Topic/Question	Contact	Expert Committee
L106	<a href="#">Margareth R.C. Marques</a> Principal Scientific Liaison	HDQ Headquarters

**Most Recently Appeared In:**

Pharmacopeial Forum: Volume No. 45(2)

**Current DocId:** [GUID-5BC38CF6-D9E6-4B39-A835-56672A3E969F\\_2\\_en-US](#)

**DOI:** [https://doi.org/10.31003/USPNF\\_R5811\\_02\\_01](https://doi.org/10.31003/USPNF_R5811_02_01)

**DOI ref:** [p8gk5](#)

OFFICIAL