

Status: Currently Official on 15-Feb-2025
 Official Date: Official as of 01-Aug-2016
 Document Type: Reagents
 DocId: GUID-4DC49AC4-6269-4217-AB21-6213C2FE9D5D_1_en-US
 DOI: https://doi.org/10.31003/USPNF_R5769_01_01
 DOI Ref: 02lx9

© 2025 USPC
 Do not distribute

L97

—Weak cation-exchange resin consisting of a highly cross-linked core of 5.5- μm porous particles having a pore size of 2000 Å units and consisting of ethylvinylbenzene cross-linked with 55% divinylbenzene. Substrate is surface grafted with carboxylic acid functionalized groups. Capacity NLT 2400 μEq /column (4-mm \times 25-cm).

Auxiliary Information - Please [check for your question in the FAQs](#) before contacting USP.

Topic/Question	Contact	Expert Committee
L97	Margareth R.C. Marques Principal Scientific Liaison	HDQ Headquarters

Most Recently Appeared In:

Pharmacopeial Forum: Volume No. PF 41(2)

Current DocId: [GUID-4DC49AC4-6269-4217-AB21-6213C2FE9D5D_1_en-US](#)

DOI: https://doi.org/10.31003/USPNF_R5769_01_01

DOI ref: [02lx9](#)

OFFICIAL