

Status: Currently Official on 16-Feb-2025
Official Date: Official as of 01-Dec-2024
Document Type: Reagents
DocId: GUID-95B09C8A-9148-4DD1-8314-ECD5F4060746_2_en-US
DOI: https://doi.org/10.31003/USPNF_R8198_02_01
DOI Ref: nvxdw

© 2025 USPC
Do not distribute

Add the following:

▲ Polyethylene Glycol 6000

$(C_2H_6O_2)_n$ average molecular weight 5400–6600 CAS RN[®]: 25322-68-3.—White to cream powder or flakes.

Viscosity: 200–270 mPas (50%, Water at 20°)

Hydroxyl value: 17–21 mg KOH/g▲ (USP 1-Dec-2024)

Auxiliary Information - Please [check for your question in the FAQs](#) before contacting USP.

Topic/Question	Contact	Expert Committee
POLYETHYLENE GLYCOL 6000	Margareth R.C. Marques Principal Scientific Liaison	HDQ Headquarters

Most Recently Appeared In:

Pharmacopeial Forum: Volume No. 49(3)

Current DocID: [GUID-95B09C8A-9148-4DD1-8314-ECD5F4060746_2_en-US](#)

DOI: https://doi.org/10.31003/USPNF_R8198_02_01

DOI ref: [nvxdw](#)

OFFICIAL