

Status: Currently Official on 16-Feb-2025
Official Date: Official Prior to 2013
Document Type: Reagents
DocId: GUID-6AC7CEEF-03EE-4001-BBA9-08CD80A2E611_1_en-US
DOI: https://doi.org/10.31003/USPNF_R3596_01_01
DOI Ref: nt2i0

© 2025 USPC
Do not distribute

S1C

—A support prepared from crushed firebrick and calcined or burned with a clay binder above 900° with subsequent acid-wash. It may be silanized.

Auxiliary Information - Please [check for your question in the FAQs](#) before contacting USP.

Topic/Question	Contact	Expert Committee
S1C	Margareth R.C. Marques Principal Scientific Liaison	HDQ Headquarters

Most Recently Appeared In:

Pharmacopeial Forum: Volume No. Information currently unavailable

Current DocID: [GUID-6AC7CEEF-03EE-4001-BBA9-08CD80A2E611_1_en-US](#)

DOI: https://doi.org/10.31003/USPNF_R3596_01_01

DOI ref: [nt2i0](#)

OFFICIAL