

Status: Currently Official on 16-Feb-2025  
Official Date: Official Prior to 2013  
Document Type: Reagents  
DocId: GUID-E7C185F1-5C65-4CF7-AF8C-65C2124F9522\_1\_en-US  
DOI: [https://doi.org/10.31003/USPNF\\_R2399\\_01\\_01](https://doi.org/10.31003/USPNF_R2399_01_01)  
DOI Ref: 259zz

© 2025 USPC  
Do not distribute

## Sand, Standard 20- to 30-Mesh

—Silica sand, composed almost entirely of naturally rounded grains of nearly pure quartz. Predominantly graded to pass an 850- $\mu\text{m}$  (No. 20) sieve (85 to 100 percentage passing) and be retained on a 600- $\mu\text{m}$  (No. 30) sieve (0 to 5 percentage passing).

[NOTE—A suitable grade is available as Ottawa Standard Sand from Thomas Scientific, 99 High Hill Road at I-295, P.O. Box 99, Swedesboro, NJ 08085-0099.]

**Auxiliary Information** - Please [check for your question in the FAQs](#) before contacting USP.

Topic/Question	Contact	Expert Committee
SAND, STANDARD 20- TO 30-MESH	<a href="#">Margareth R.C. Marques</a> Principal Scientific Liaison	HDQ Headquarters

**Most Recently Appeared In:**

Pharmacopeial Forum: Volume No. Information currently unavailable

**Current DocId:** [GUID-E7C185F1-5C65-4CF7-AF8C-65C2124F9522\\_1\\_en-US](#)

**DOI:** [https://doi.org/10.31003/USPNF\\_R2399\\_01\\_01](https://doi.org/10.31003/USPNF_R2399_01_01)

**DOI ref:** [259zz](#)

OFFICIAL